

HTM ESMALTE AZULEJOS BLANCO



FAMILY HTM / SISTEMAS TINTOMÉTRICOS
LINE PINTURAS MAGICAS

DESCRIPTION AND NATURE

Polyurethane lacquer enamel for painting bathroom and kitchen tiles. Gloss finish. Provides a high-quality finish, with excellent hardness and scratch resistance. Fully washable.

USAGES

- Kitchens and bathrooms of indoor areas.
 Outdoor/Indoor
 Tiles

PROPERTIES

Strongness
 Makes a film
 Penetration power
 Strong resistance to the atmospherical factors
 Self-leveling
 Penetration power
 Strong resistance to the atmospherical factors
 -Scratch resistance.
 Good applicability
 No cracking at all
 Does not form blisters
 Odourless when dry
 Washable

TECHNICAL CHARACTERISTICS

Referencia Color	HTM ESMALTE AZULEJOS BLANCO
Finish	Gloss
Specific weight	1,04± 0,05 kg/l
Viscosity	75 +/- 5 KU
Solids in volume	45± 1
Solids in weight	61± 1
VOC	Cat. I/BD 600/500 (2007/2010): 492,65 g/l
Aproximated performance by coat	12-16 m²/L
Dry to touch	(20°C HR: 60%): 2-3 h
Dry to repaint	(20°C HR: 60%): 24 h
Colours	White, Iceland grey, off-white, sea water, cherry red, warm beige and raw Sienna.

SURFACE PREPAIRING

French norm DTU 59.1

New surfaces

Restoring and maintenance

Ceramic tiles:

1. The surface to be painted must be free from foreign products and/or residues, grease- and dust-free and dry. Wash with

HTM ESMALTE AZULEJOS BLANCO

- soap and water. Do not use silicone- or wax-based cleaning products.
2. Clean tile joints with a brush and subsequently remove any remaining residues.
 3. Shade tiles to improve adhesion and clean with a damp cloth.
 4. Remove any traces of residue and dry using a dry cloth.

WAY OF USE

Application Notes

- The tile must be free from foreign products and/or residues, well-cleaned, dust-free and dry. Wash with soap and water. Do not use silicone- or wax-based cleaning products.
- Clean tile joints with a brush and subsequently remove any remaining residues.
- Stir the product until perfectly blended.
- Apply according to the instructions set out in the attached application table. - When applying the first coat dilute the product according to the porosity and state of the surface. Finish with one or more coats until full coverage is achieved. Apply the product in fine coats, spreading it appropriately until the surface is uniformly covered.
- Do not apply to floors or worktops. Do not apply to submerged areas
- Do not apply the product when room temperature is under 5°C or to surfaces exposed to strong sunlight.
- Ensure the area is well ventilated while the product is drying.
- Do not apply when relative moisture is over 80%.
- Store the paint in a place protected from the elements and low temperatures.
- Clean utensils with solvents immediately after use.
- Take certain precautions during the first days after the paint is applied. Do not wash or touch until at least seven days have elapsed.
- Do not use abrasives or scourers which might scratch the enamel.
- Hardness, adhesion and ultimate resistance are obtained after 21 days.

Solvent for dilution and cleaning

Solvent 1401, 1408

Way of use	Aproximate dilution
Painting brush	0-10%
Roller	0-10%
Spray gun	15-25%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Tiles, Ceramic Material			
MAX	HTM Esmalte Azulejos	HTM Esmalte Azulejos	HTM Esmalte Azulejos
STD	HTM Esmalte Azulejos		HTM Esmalte Azulejos

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

501979

Fecha de Alta

05-01-2016

Versión

3 - 20/03/2018

HTM ESMALTE AZULEJOS BLANCO



PACKINGS

2.5 L

Canned bases 0.75 L